BAKHTI Software Ltd
Civil engineering software development
Website: https://www.bakhtisoftware.com
Email: bakhti@bakhtisoftware.com/ support@bakhtisoftware.com

Project: RN 18 Project No.: Ref 004/2022

Client: SARL EGN
Location: Medea
Date: 2020-03-03

DETERMINATION OF BINDER CONTENT FOR ASPHALT MIX
Standard: NF EN 12697-1

Test: Kumagawa N=1
Company: ENTP
Quarry: Sidi Moussa
Bitumen grade: 40/50
Fraction: BBSG 0/14
Destination: BB 0/14

The mass of dry specimen before extraction, expressed in grams (g)- M1	**150,00**
The mass of dry specimen after extraction, expressed in grams (g)- M2	**141,00**
The content of soluble external binder, expressed as a percentage (%)- CBext	**6,38**
The content of soluble inner binder, expressed as a percentage (%)- CBint	**6,00**

The content of target binder: 6,00 %
Accepted result