BAKHTI Software Ltd
Civil engineering software development
Website: https://www.bakhtisoftware.com
Email: bakhti@bakhtisoftware.com/ support@bakhtisoftware.com

Project:

Client:
Location:
Date: 2026-09-19

MICRO - DEVAL ABRASION TEST

Standard: NA 5129

Test: Micro-Deval N°=1
Sample mass: 500 g
Testing type: With water

Granular class	Abrasive load (g)	Dry mass of sieve retained (g)	Dry mass of passing (g)	% loss	% loss (Average)
10/14	5000	375,00	125,00	25,00	**23,33**
		383,00	117,00	23,40	
		392,00	108,00	21,60	

Requirements: M.D. abrasion loss ≤ 25,00 %

Results:
- Acceptable value
- Material accepted