BAKHTI Software Ltd
Civil engineering software development
Website: https://www.bakhtisoftware.com
Email: bakhti@bakhtisoftware.com/ support@bakhtisoftware.com

Project:

Client:
Location:
Date: 2026-09-19

TEST SAND EQUIVALENT

Standard: NA 455

Test: Sand equivalent N°=1
Granular class: 0/3

N° Sample	h1 (cm)	h2 (cm)	SE (%)	SE Average (%)
1	12,00	9,20	76,67	**78,06**
2	12,00	9,50	79,17	
3	12,00	9,40	78,33	

Requirements: SE ≥ 70,00

Results:
- Acceptable value
- Material accepted