



# BAKHTI Software Ltd

## Civil engineering software development

Website: <https://www.bakhtisoftware.com>

Email: [bakhti@bakhtisoftware.com](mailto:bakhti@bakhtisoftware.com) / [support@bakhtisoftware.com](mailto:support@bakhtisoftware.com)

Project: Suivi RN 18

Project No.: Ref 008/2020


Client: DTP

Location: Medea


Date: 2023-03-05

### TEST REPORT

CBR Test NF P 94-078



$\gamma_d$ (kN/m <sup>3</sup> )	$\omega$ (%)	Penetration		CBR (%)
		2.5 mm	5 mm	
19,85	4,20	10,23	19,02	95,43
18,50	6,20	3,60	11,04	55,39
18,10	7,10	5,43	9,12	45,76




---

---

---

---

---

---

---

---

---

---



# BAKHTI Software Ltd

## Civil engineering software development

Website: <https://www.bakhtisoftware.com>

Email: [bakhti@bakhtisoftware.com](mailto:bakhti@bakhtisoftware.com) / [support@bakhtisoftware.com](mailto:support@bakhtisoftware.com)

Project: Suivi RN 18

Project No.: Ref 008/2020


Client: DTP

Location: Medea

Date: 2022-10-16

### TEST REPORT

CBR Test NF P 94-078



Type: Immediate bearing ratio  
 $\gamma_d = 18,2 \text{ kN/m}^3$   
 $\omega = 4,2 \%$   
 Correction = 0 mm  
 CBR= 95,43

<b>Penetration Depth (mm)</b>	0,000	0,625	1,250	2,000	2,500	5,000	7,500	10,000
<b>Load (kN)</b>	0,000	2,510	4,920	8,210	10,230	19,020	24,100	26,200