



BAKHTI Software Ltd
Civil engineering software development
Website: <https://www.bakhtisoftware.com>
Email: bakhti@bakhtisoftware.com / support@bakhtisoftware.com

Project: Suivi RN 18

Project No.: Ref 008/2020

Client: DTP
Location: Medea
Date: 2020-03-06

CONCRETE COMPRESSION TEST

Standard: ASTM C39

Test: Compression N=1
Made up : The site
Destination of concrete: EPTP

Concrete Mix Design	Material	Dosage (kg/m ³)	Material	Dosage (kg/m ³)
	Sand	945	Cement	350
	Gravel 01	480	Water	195
	Gravel 02	405	/	/

Shape and dimensions of specimens: 16x32 Cylindrical
Slump for the given sample : 6
Storage conditions: Under water
Temperature: 20c
Press machine class: A

Specimen Specimen	Pouring date	Test date	Age (D)	Mass (kg)	Failure load (kN)	Compressive strength (bars)	Average (bars)
1	01/02/2020	08/02/2020	7	15,12	360	180	180,0
2				15,09	350	175	
3				15,21	370	185	
4	01/02/2020	29/02/2020	28	15,14	500	250	258,3
5				15,16	520	260	
6				15,23	530	265	

N.B: